



# Inspection Report - Dry Film Thickness

KMK\  
KMK POVELS

## Individuals / Run Chart



## Histogram



## Notes

KMK NOSIOC: P 000480

<b>Project Name</b>	KMK
<b>Gauge Type</b>	Elcometer 456/4
<b>PCB Serial #</b>	
<b>Serial #</b>	PC01367
<b>User ID</b>	
<b>Probe Type</b>	F1
<b>Serial #</b>	PC00989
<b>Calibration Method</b>	Smooth
<b>Type</b>	F1
<b>Date</b>	14.4.2014. 14:20
<b>Thick Foil</b>	250,0
<b>Thin Foil</b>	0,0
<b>Batch Name in Gauge</b>	KMK POVELS
<b>User ID</b>	KMK POVELS
<b>Created Date</b>	5.5.2014. 9:12:04
<b>Updated Date</b>	5.5.2014. 9:12:04
<b>First Reading Date</b>	5.5.2014. 9:13:01
<b>Last Reading Date</b>	5.5.2014. 9:32:03

<b>Statistics # Readings</b>	60
<b>Mean</b>	332,43 µm
<b>Maximum</b>	405,0 µm
<b>Minimum</b>	281,0 µm
<b>Standard Deviation (σ)</b>	29,80 µm
<b>Mean + 3σ</b>	421,84 µm
<b>Mean - 3σ</b>	243,02 µm
<b>Coefficient of Variation</b>	9,0%